MRO Delay Line


Specification of the Science and Metrology Windows for the MROI Delay Lines

INT-406-TSP-0004

The Cambridge Delay Line Team

rev 1.0

18 March 2010



Cavendish Laboratory JJ Thomson Avenue Cambridge CB3 0HE UK

Change Record

Revision	Date	Author(s)	Changes
0.1	2009-05-27	MF	Initial draft
0.2	2010-01-26	MF	Corrections
0.3	2010-02-25	MF	Revised wave-front spec to be on transmitted beam rather
			than surfaces because Infrasil 301 can still have significant
			refractive index variations.
			Placed parallelism spec on metrology windows
1.0	2010-03-18	MF	Revised science window transmitted wave-front spec to
			1/10 th wave to be consistent with optical budget. Revised
			metrology window parallelism to 1 arc-minute.

Objective

To present the manufacturing specifications for the science and metrology windows for the MROI delay lines.

Scope

The specifications produced are for the science window and the two metrology windows of the delay line. The science window specification also covers the windows that would be introduced to preserve the vacuum when the removable section of the beam relay pipe is not installed. The science window specification also covers the window at the telescope end of the beam relay pipe.

Reference Documents

RD1 Top Level Requirements INT-406-TSP-0002

RD2 MROI Delay Line Derived requirements INT-406-VEN-0107

RD3 Draft window specifications for the MROI delay lines

RD4 Internal memo on parallelism requirement of science windows

Applicable Documents

AD1 Drawing of science window

AD2 Drawing of metrology window

Acronyms and Abbreviations

BCA	Beam Combining Area		
BCF	Beam Combining Facility		
BRS	Beam Relay System		
DL	Delay Line		
DLA	Delay Line Area		
ICD	Interface Control Document		
ICS	Interferometer Control System (now SCS		

MROI Magdelena Ridge Observatory
Interferometer
MRAO Mullard Radio Astronomy Observatory

NMT New Mexico Tech
OPD Optical Path Delay

SCS Supervisory Control System

TBC To be confirmedTBD To be determined

Table of Contents

1	Introduct	ion	4
2	Science V	Vindow	4
		nce Window Requirements	
		nce Window Specifications	
	2.2.1	Dimensions	
2.2.2 Optical quality 2.2.3 Material 2.2.4 Coating 2.2.5 Suitable suppliers		Optical quality	
		Material	
		Coating	
		Suitable suppliers	
		y Window	
		rology window requirements	
		rology Window Specifications	
3.2.1 D		Dimensions	
		Optical quality	
	3.2.3	Material	
	3.2.4	Coating	
	3.2.5	Suitable suppliers	
4		~ #	

1 Introduction

The science and metrology windows have differing requirements but are present here in one document. The science window is approximately 150mm in diameter and the metrology window is approximately 50mm in diameter. Both are subject to vacuum on one side and atmospheric pressure on the other. The science window must operate over a wide waveband while the metrology window need only operate at the laser wavelength and therefore the coatings are quite different. The science window specification is also suitable for the beam relay windows.

2 Science Window

2.1 Science Window Requirements

The requirements of the science window and the justification for most of the design parameters are presented in RD3. The requirement on parallelism of the window is set out in RD4 and further requirements are specified in RD2.

An additional requirement is placed on the tolerance of the thickness of the window in order to achieve a suitable vacuum seal from a single design. Although for reasons of longitudinal dispersion the windows should be matched to 0.5mm in thickness, the mechanical design of the window holder requires a tolerance of ± 0.1 mm to be adhered to. Note that normally just two science windows would be used giving a total of 30mm in thickness but at times a further two windows would be introduced, doubling this thickness, when a section of beam relay pipe is removed.

2.2 Science Window Specifications

The following subsections list the detailed manufacturing specifications for the science windows.

2.2.1 Dimensions

Circular with diameter 150mm ±0.25mm Clear aperture required: 140mm Thickness 15mm ±0.1mm Chamfer 1mm at 45° both edges

2.2.2 Optical quality

Transmitted wave-front quality: lambda/10 (633nm, peak-valley) over any 125mm diameter patch within the clear aperture.

Surface quality: 40-20 scratch dig, or better

Surface parallelism: 10 arc-seconds

Sub-surface damage: consistent with surface quality and safety for operation as a vacuum window.

2.2.3 Material

INFRASIL 301

2.2.4 Coating

No coating

2.2.5 Suitable suppliers

ICOS, OSL (see section 4)

3 Metrology Window

3.1 Metrology window requirements

3.2 Metrology Window Specifications

3.2.1 Dimensions

Circular with diameter $50\text{mm} \pm 0.2\text{mm}$ Clear aperture required Thickness $10\text{mm} \pm 0.1\text{mm}$ Chamfer 0.5mm at 45° both edges unless stock item

3.2.2 Optical quality

Surface figure: lambda/10 or better for each face Surface quality: 60-40 scratch dig, or better Surface parallelism: 1 arc-minute or better

3.2.3 Material

BK7 or fused silica

3.2.4 Coating

MgF₂ ¹/₄ wave at 633nm

3.2.5 Suitable suppliers

Melles-Griot

4 Suppliers

IC Optical Systems Ltd 190-192 Ravenscroft Road Beckenham Kent BR3 4TW United Kingdom

Optical Surfaces Limited

Godstone Road Kenley Surrey CR8 5AA ENGLAND